

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
3 February 2005 (03.02.2005)

PCT

(10) International Publication Number
WO 2005/010896 A1

(51) International Patent Classification⁷: **H01B 3/44**,
C08L 23/04, H01B 7/00, 17/62

(21) International Application Number:
PCT/US2004/023723

(22) International Filing Date: 22 July 2004 (22.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/490,314 24 July 2003 (24.07.2003) US

(71) Applicant (for all designated States except US): **UNION
CARBIDE CHEMICALS & PLASTIC TECHNOL-
OGY CORPORATION** [US/US]; 39 Old Ridgebury
Road, Danbury, CT 06817-0001 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **GROSS, Laurence, H.**
[US/US]; 977 Rector Road, Bridgewater, NJ 08807 (US).

(74) Agent: **HANSBRO, Kevin, R.**; The Dow Chemical Com-
pany, Intellectual Property, P.O. Box 1967, Midland, MI
48641-1967 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): **AF, AG, AL, AM,**
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GI, GL, GM, GR, GU, HT, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): **ARIPO** (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), **Eurasian** (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), **OAPI** (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **CABLE INSULATION SYSTEM WITH FLEXIBILITY, HIGH TEMPERATURE DEFORMATION RESISTANCE,
AND REDUCED DEGREE OF STICKINESS**

(57) Abstract: The present invention is a cable comprising one or more electrical conductors or a core of one or more electrical con-
ductors and having each conductor or core being surrounded by a layer of insulation. The insulation comprises an olefinic polymer,
having a density in the range of 0.880 to 0.915 grams per cubic centimeter, a melting temperature of at least 115 degrees Celsius,
a melt index in the range of 0.5 to 10 grams per 10 minutes, a crystallization-analysis-soluble fraction in 1,2,4-trichlorobenzene at
30 degrees Celsius of less than 35 weight percent, and a polydispersity index of at least 3.5. Alternatively, the insulation layer has
an 1% secant flexural modulus at ambient of less than 15,000 psi and a dynamic elastic modulus at 150 degrees Celsius of at least
4x10⁷ dyne/square centimeter.

WO 2005/010896 A1